

# DULUX<sup>®</sup> AUTOSPEED<sup>®</sup> 440 Line PT Solid, Metallic & Pearlescent Basecoat Tinters



Dulux Australia  
ABN 67 000 049 427

440 Line Dulux<sup>®</sup> AUTOSPEED<sup>®</sup> PT Solid, Metallic & Pearlescent t Base Coat Tinters

## Product Name:









440 Line Dulux<sup>®</sup> Autospeed<sup>®</sup> PT Metallic and Pearlescent Base Coat Tinters

## Product Description:

Dulux<sup>®</sup> Autospeed<sup>®</sup> PT Tinters are a premium range of high quality single pack metallic, pearlescent and solid colour basecoat tinters developed for automotive refinishing. This range has been developed as a quick drying colour base coat for spot repairs and overall work. These products should be top coated with Dulux<sup>®</sup> Autospeed<sup>®</sup> clear coat range.

## Product & Additives:

Dulux<sup>®</sup> Autospeed<sup>®</sup> PT Tinters 440 Line  
 Dulux<sup>®</sup> Autospeed<sup>®</sup> PT Flat base 485-89898  
 Dulux<sup>®</sup> Autospeed<sup>®</sup> Standard Thinner 920-89909  
 Dulux<sup>®</sup> Autospeed<sup>®</sup> Low Temp Thinner 920-89908 (Small areas & Colder Temperatures)  
 Dulux<sup>®</sup> Autospeed<sup>®</sup> High Temp Thinner 920-89910 (High Temperatures)

	<b>Mixing Ratio</b>	1 part by weight 440 line colour
	<b>Thinner</b>	1 part by weight 920-89909 OR 920-89908 920-89910 High Temperatures
	<b>Spray Viscosity</b> DIN Cup 4 @ 25°C	14 seconds (100% thinner)
	<b>Gravity Feed</b>	<b>Fluid Tip:</b> CONVENTIONAL: 1.2 - 1.5mm HVLP: 1.5 - 1.9mm <b>Spraying Pressure:</b> 400 kPa/4 bar 200 kPa/2 bar Or refer to manufacturer's recommendations
	<b>Suction Feed</b>	CONVENTIONAL: 1.4 - 1.8mm HVLP: 1.8 - 2.0mm 400 kPa/4 bar 200 kPa/2 bar Or refer to manufacturer's recommendations
	<b>Application</b>	Single wet coats
	<b>Air Flash</b>	3 - 5 minutes air flash
	<b>Spraying</b>	Use air fed mask at all times. Refer applicable AS/NZS Standards

# DULUX® AUTOSPEED® 440 Line PT Solid, Metallic & Pearlescent Basecoat Tinters



Dulux Australia  
ABN 67 000 049 427

## Recommendation:

Dulux recommend the complete painting of panels to provide maximum durability when applying topcoats such as clear coats. Blend outs will not give the appropriate film builds required and may break down prematurely.

## For Safe Handling:

Please refer to the Material Safety Data Sheet No: 434 for this product before use. This product may contain materials that are being introduced to Australia under a permit.

**In the event of an emergency contact: 1 800 033 111 (ALL HOURS)**

## For further information contact:

**Dulux Australia**  
1956 Dandenong Rd, Clayton,  
Victoria, 3168  
Australia

ABN 67 000 049 427

**Telephone:**  
1 800 810 114

**Fax:**  
61 3 8787 4502

**Dulux New Zealand**  
31B Hillside Road  
Glenfield, Auckland  
New Zealand

**Telephone:**  
0800 800 424

Dulux and Autospeed are registered trademarks. Marks followed by the symbol ™ are trademarks.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by Dulux Refinish Coatings in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux Refinish Coatings to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux Refinish Coatings provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux Refinish Coatings by any condition or warranty implied by applicable legislation, regulation or other Government ordinance voiding or prohibiting such exclusion, limitation or modification